

Physical properties PA 66 Nylatron GS

Properties	Test methods	Units	Values
Colour	-	-	gray-black
Density	ISO 1183-1	g/cm ³	1.15
Water absorption: after 24/96 h immersion in water of 23°C	ISO 62	mg	46 / 85
at saturation in air of 23°C / 50% RH	ISO 62	%	0.68 / 1.25
at saturation in water of 23°C	-	%	2.3
	-	%	7.8
Thermal Properties			
Melting temperature (DSC, 10° C/min.)	ISO 11357-1/-3	°C	260
Glass transition temperature (DSC, 20°C/min)	ISO 11357-1/-2	°C	-
Thermal conductivity at 23°C	-	W/(K.m)	0.29
Coefficient of linear thermal expansion: average value between 23 and 60°C	-	m/(m.K)	80 x 10 ⁻⁶
average value between 23 and 100°C	-	m/(m.K)	90 x 10 ⁻⁶
Temperature of deflection under load: method A: 1.8 MPa	+ ISO 75-1/-2	°C	85
Max. allowable service temperature in air: for short periods	-	°C	180
continuously: for 5'000 / 20'000 h	-	°C	95 / 80
Min. service temperature	-	°C	-20
Flammability: „Oxygen Index“ according to UL 94 (3 / 6 mm thickness)	ISO 4589-1/-2	%	26
	-	-	HB / HB
Mechanical Properties at 23°C			
Tension test: tensile stress at yield / tensile stress at break	+ ISO 527-1/-2	MPa	93 / -
	++ ISO 527-1/-2	MPa	56 / -
Ttensile strength	+ ISO 527-1/-2	MPa	95
tensile strain at yield	+ ISO 527-1/-2	%	5
tensile strain at break	+ ISO 527-1/-2	%	20
	++ ISO 527-1/-2	%	> 50
tensile modulus of elasticity	+ ISO 527-1/-2	MPa	3600
	++ ISO 527-1/-2	MPa	1725
Compression test: compressive stress at 1 / 2 / 5% nominal strain	+ ISO 604	MPa	32 / 62 / 100
Charpy impact strength - unnotched	+ ISO 179-1/1eU	kJ/m ²	no break
Charpy impact strength - notched	+ ISO 179-1/1eA	kJ/m ²	4
Ball indentation hardness	+ ISO 2039-1	N/mm ²	165
Rockwell hardness	+ ISO 2039-2	-	M88
Electrical Properties at 23°C			
Electrical strength	+ IEC 60243-1	kV/mm	26
	++ IEC 60243-1	kV/mm	17
Volume resistivity	+ IEC 60093	Ohm.cm	> 10 ¹⁴
	++ IEC 60093	Ohm.cm	> 10 ¹²
Surface resistivity	+ IEC 60093	Ohm	> 10 ¹³
	++ IEC 60093	Ohm	> 10 ¹²
Relative permittivity ε _r : - at 100 Hz	+ IEC 60250	-	3.8
	++ IEC 60250	-	7.4
- at 1 MHz	+ IEC 60250	-	3.3
	++ IEC 60250	-	3.8
Dielectric dissipation factor δ tan: - at 100 Hz	+ IEC 60250	-	0.013
	++ IEC 60250	-	0.13
- at 1 MHz	+ IEC 60250	-	0.020
	++ IEC 60250	-	0.06
Comparative tracking index (CTI)	+ IEC 60112	-	600
	++ IEC 60112	-	600

+ : Values for dry material
 ++ : Values for up to saturation
 in air of 23° C / 50%
 RF material stored (mostly
 derived from large)

This table is a valuable help in the
 choice of a material. The data
 listed here fall within the normal
 range of products properties, but
 they should not be used to
 establish material specification
 limits nor used alone as the basis
 of design.

Note: 1 g/cm³ = 1000 kg/m³; 1 Mpa = 1 N/mm²; 1 kV/mm = 1 MV/m.